

CLAIMS

1. An ointment patch comprising a support, an ointment,
(and optionally, a separator) wherein the ointment is coated
on one surface of the support in an amount of 0.1mg to

5 200mg per 1cm² of the support and the support has a
thickness of 1µm to 2000µm and 50% modulus of 5g/cm to
600g/cm.

2. The ointment patch according to claim 1, wherein the
support has a water vapor permeability of 100g/m²/24hrs or
10 higher.

3. The ointment patch according to claim 1 or 2, wherein
the support is composed of a copolymer of vinyl acetate and
acrylic acid, the copolymer obtained by copolymerizing a
vinyl acetate, an alkyl ester of a (meth)acrylic acid with
15 the alkyl having 4 to 14 carbon atoms on average, and a
(meth)acrylic acid in amounts of 0 to 90wt%, 10 to 97wt%,
and 0 to 15wt%, respectively, and the copolymer is cross-
linked.

4. The ointment patch according to any one of claims 1
20 to 3, wherein the support is formed from film overlaid with
cloth.

5. The ointment patch according to any one of claims 1
to 4, wherein the support is non-ointment-migration-
permissive.

25 6. The ointment patch according to any one of claims 1

SB
a2

to 5, wherein the support includes an adhesive layer disposed on the ointment-coated surface of the support in order to allow the ointment patch to adhere to skin with a part of the patch.

5 7. The ointment patch according to any one of claims 1 to 6, wherein the ointment patch is folded onto itself to bring the ointment-coated surface into contact with itself.

8. An ointment applicator comprising a support, and an adhesive layer disposed on one surface of the support to
10 allow the ointment applicator to adhere to skin with a part of the applicator, wherein the support has a thickness of 1mm to 2000mm and 50% modulus of 5g/cm to 600g/cm.

9. The ointment applicator according to claim 8, wherein the support has water vapor permeability of 100g/m²/24hrs
15 or higher.

10. The ointment applicator according to claim 8 or 9, wherein the support is composed of a copolymer of a vinyl acetate and an acrylic acid, the copolymer obtained by copolymerizing a vinyl acetate, an alkyl ester of a
20 (meth)acrylic acid with the alkyl having 4 to 14 carbon atoms on average, and a (meth)acrylic acid in amounts of 0 to 90wt%, 10 to 97wt%, and 0 to 15wt%, respectively, and the copolymer is cross-linked.

11. The ointment applicator according to any one of
25 claims 8 to 10, wherein the support is formed from film

overlaid with cloth.

12. The ointment applicator according to claim 8 to 11,
wherein the support is non-ointment-migration-permissive.

10034409.014802